## **IORAWLPLUG**®

## **R-RPS-K Polyurethane Foam All Season**

Low-pressure, one-component polyurethane foam with delivery tube

## **Product information**



## Applications

- Fixing pipes and cables in HVAC systems
- The application of PU foam: installation of windows and doors, filling, sealing, insulation in the construction industry
- Installation of windows and door
- Easy fixing of door and window frames timber, metal or PVC
- Fixing (for installation of doors and windows)
- Thermal insulation of roofing (including flat roofs)
- Installation & sealing of window sills
- Thermal insulation of plumbing and central heating
- Filling gaps in the thermal insulation of buildings
- Filling frame structures

### Features and benefits

- Ideal for mounting, sealing and soundproofing.
- Excellent sound and thermal insulation properties.
- Resistant to mould and fungi.

### **Base materials**

#### Approved for use in:

- Concrete
- Masonry
- Wood
- Metal Sheet & Profiles
- PVC Profile
- Window Profile

## **Installation guide**



1. Wear protective gloves. Ensure surfaces are free from dust, dirt or debris.

- 2. Remove the frost from the working surface.
- 3. Before using, make sure that the can temperature is above zero (optimum +20°C). Application temperature from -10°C up to +30°C.

4. Shake can vigorously for 30 seconds to mix properly components.

- 5. Screw straw-applicator onto the can. Hold can upside-down during application.
- 6. Fill gaps from down to up, zigzag motion, alternating from one wall to the other. Fill gaps to approximately 60 % volume. Max. wide of the gap 5 cm. Gaps wider than 5 cm should be applied after hardening of the previous layer.
- 7. After full curing, cut the excess foam with a knife and protect it from UV exposure by coating with plaster, paint, acrylic or silicone.

# 

## **Technical Data**

Parameter		Value	Methods		
Application temperature	[°C]	-10 ÷ +30			
Can temperature	[°C]	+20			
Efficiency	[dm³]	max. 40			
Colour	-	Light yellow			
Skin formation time	[min]	5 ÷ 12	20°C, RH 90%		
Pretreatment time	[min]	60	20°C, RH 90%		
Complete hardening time	[h]	24			
Fire resistance class	-	В3	DIN 4102		
Density	[kg/m <sup>3</sup> ]	26 ± 10	PN-EN ISO 845:2000		
Dimensional stability	[%]	≤5	40°C, RH 95%, 24 hrs		
Water absorption after 24h	[kg/m <sup>3</sup> ]	≤2	PN-EN 1609:1999		
Tensile strength	[kPa]	≥ 100	PN-EN 1607:1999		
Compressive strength	[kPa]	≥ 50	PN-EN 826:1998		
Thermal resistance (upon hardening)	[°C]	-50 ÷ +90			
Preparations solublity	-	Acetone, before hardening	Cleaner RPC-0500		
Soundproofing coefficient	[dB]	61	EN 12354-3		
Volume	[ml]	660			
VOC Content	[%]	7,68	calculated value		

Parameter		Value			
Shelf life [month]		18			
	-	upright position in an originally closed container			
		the storage temperature: from +5°C to +35°C (room temperature is recommended)			
Storage conditions		dry, cool and well-ventilated place away from direct sunlight and other sources of heat and ignition			
		storing the product in conditions other than recommended may shorten the lif me even by 3 months			

## Product commercial data

Product Code Colour	Maluma fmll	Quantity [pcs]			Weight [kg]			Bar Codes	
	Colour	Colour Volume [ml]	Box	Outer	Pallet	Box	Outer	Pallet	Bai Codes
R-RPS-K	Light yellow	660	12	12	672	10.9	10.9	642.2	5906675430058

2