

R-SL-SKL Glass Silicone

Glass silicone - One-component, elastic sealant with acetate curing system.

Product information



Applications

- For standard glazing applications, as well as hotboxes for gardening.
- Sealant for glass-to-glass applications.
- Installation of cabinets, cupboards, shop-windows, glass displays, etc.
- Suitable for joining of: aluminum, brass, copper, steel, galvanized steel, plastic, concrete and many other materials.
- Do not use for fish tanks, mirrors, or for bonding natural stone surfaces.
- · Joints are mould resistant.

Features and benefits

- Highly and permanently elastic sealing properties, with excellent resistance to water, grease, acids and alkalis.
- Very good adhesion to materials and substrates used commonly in construction: glass, tiles, ceramics and protected metals
- Durable seal (completely resistant to weathering and UV radiation)

Base materials

Approved for use in:

- Glass
- Metal Sheet & Profiles
- Stainless Steel
- Glaze
- Concrete
- Protected wood
- Plastics
- Protected metals (aluminium, brass, copper, steel, zinc-plated metal sheet)

Installation guide







- 1. The surface, that silicone will be apllied on, should be clean, free of dust, grease, rust, remains of old seal and other substances that might weaken the cohesion.
- 2. Prior to application of silicone protect edges with masking tape
- 3. Cut the tip of the cartridge, leaving part of the thread. Screw the applicator on to the thread, then cut at the required angle to give an aperture width suited to the joint.
- 4. Use manual or pneumatic gun applicator.
- 5. Applied silicone may be smoothed with a spatula or similar tool. Moisten the spatula first in special wetting agent or detergent solution.
- 6. The silicone hardens by reaction with moisture from the air, so ensure well-ventilated conditions.
- 7. After completing the application, wipe tools with a paper towel and clean with solvent.



Technical Data

Parameter		Value	Methods	
Application temperature	[°C]	+5 ÷ +40		
Coverage	-	18 linear meters of 4x4 mm joint per one 300 ml cartridge		
Thermal resistance (upon hardening)	[°C]	-40 ÷ +180		
Pretreatment time	[min]	25		
Curing time	[mm/24h]	2		
Hardening system	-	one-component-crosslinking with air humidity		
Hardening type	-	acidic-acetate		
Density	[kg/dm³]	0.98-1.05		
Shore A hardness	-	18	SHORE A Method, after 14 days	
Ultimate elongation	[%]	150	ISO 8339, +23°C	
Shrinkage	[%]	17		
Allowable deformation	[%]	15		
Packaging	-	300 ml cartridge		
R-SL-SKL-01				
Colour	-	transparent		
R-SL-SKL-02				
Colour	-	white		

Parameter		Value		
Storage temperature [°C]		+5 ÷ +35		
Storage	[month]	18		
	-	In originally closed containers, in cool and dry places.		

Product commercial data

Product Code (Colour Box	Quantity [pcs]		Weight [kg]			Bar Codes	
		Вох	Outer	Pallet	Вох	Outer	Pallet	Bai Codes
R-SL-SKL-01	transparent	15	15	1260	5.3	5.3	477.8	5906675251189
R-SL-SKL-02	white	15	15	1260	5.3	5.3	475.5	5906675251196