# 

## **R-RPP-45 Polyurethane Gun Foam**

Low-pressure, one-component polyurethane foam with applicator gun.

### **Product information**



### Applications

- Fixing pipes and cables in HVAC systems
- The application of PU foam: installation of windows and doors, filling, sealing, insulation in the construction industry
- Installation of windows and door
- Easy fixing of door and window frames timber, metal or PVC
- Ideal for mounting, sealing and sound proofing
- Filling empty spaces, cracks, pipe passages
- Filling gaps in the thermal and acoustic insulation
- Fixing (for installation of doors and windows)
- Thermal insulation of roofing (including flat roofs)

### Features and benefits

- Suitable for use indoors and outdoors.
- Excellent sound and thermal insulation properties.
- Can be painted or plastered when cured
- Cutting time 40 min after apllication
- Yield up to 45 l
- Resistant to mould and fungi.
- Excellent adhesion to most materials and substrates used in construction.

### **Base materials**

#### Approved for use in:

- Concrete
- Masonry
- Wood
- Metal Sheet & Profiles
- PVC Profile
- Window Profile

### Installation guide



### Foams, Sealants & Adhesives

# 

- 1. Wear protective gloves. Ensure surfaces are free from dust, dirt or debris.
- 2. Before using, make sure that the can temperature is above zero (optimum +20°C). Application temperature from +5°C up to +30°C.
- 3. Shake can vigorously for 30 seconds to mix properly components.
- 4. Screw gun onto the can. Hold can upside-down during application.
- 5. Moisten surfaces with water prior to application.
- 6. Fill gaps from down to up, zigzag motion, alternating from one wall to the other. Fill gaps to approximately 60 % volume. Max. wide of the gap 3-4 cm. Wider gaps should be applied after hardening of the previous layer. Each layer should be moistened with water using a spray.
- 7. After full curing, cut the excess foam with a knife and protect it from UV exposure by coating with plaster, paint, acrylic or silicone.
- 8. In the event of a stoppage exceeding five minutes duration, wipe the nozzle with cleaner for foam applicator.
- 9. After removing the applicator gun from the can, wipe down the nozzle and gun (internal and external surfaces) using a cleaner.

### **Technical Data**

Parameter		Value	Methods		
Efficiency	[dm³]	max. 45			
Density		17-21	PN-EN ISO 845:2000		
Soundproofing coefficient		61	EN 12354-3		
Application temperature	[°C]	+5 ÷ +30			
Can temperature	[°C]	+20			
Colour	-	Light yellow			
Post-expansion		120			
Skin formation time	[min]	4÷7	20°C, RH 90%		
Pretreatment time	[min]	45	20°C, RH 90%		
Complete hardening time	[h]	24			
Fire resistance class	-	В3	DIN 4102		
Dimensional stability	[%]	1.2 - 3	40°C, RH 95%, 24 hrs		
Water absorption after 24h	[kg/m <sup>3</sup> ]	1	PN-EN 1609:1999		
Tensile strength	[kPa]	≥ 100	PN-EN 1607:1999		
Compressive strength	[kPa]	≥ 40	PN-EN 826:1998		
Thermal resistance (upon hardening)	[°C]	-50 ÷ +90			
Thermal conductivity	[W/mK]	0,038			
Preparations solublity	-	Acetone, before hardening	Cleaner RPC-0500		
Volume	[ml]	750			

Parameter		Value			
Shelf life [month]		15			
	-	upright position in an originally closed container			
		the storage temperature: from +5°C to +35°C (room temperature is recommended)			
orage conditions		dry, cool and well-ventilated place away from direct sunlight and other sources heat and ignition			
		storing the product in conditions other than recommended may shorten the life time even by 3 months $% \left( {{{\rm{T}}_{\rm{T}}}} \right)$			

### Product commercial data

Product Code Colour	Volume [ml]	Quantity [pcs]			Weight [kg]			Bar Codes	
	votume [mt	Votanie [int]	Box	Outer	Pallet	Box	Outer	Pallet	bar codes
R-RPP-45	Light yellow	750	12	12	672	10.9	10.9	639.5	5906675284996

2