

# R-SL-TK-EN High Temperature Silicone

High-temperature silicone – One-component elastic sealant with acetate curing system.

## Product information



### Applications

- Sealing in high-temperature environments: furnaces, chimneys, heating installations, combustion & fuel ducts, ventilation and air-conditioning systems.
- Fixing of elements in domestic fireplaces and industrial furnaces.

### Features and benefits

- The seal possesses complete and long-term resistance to oils, petrol, grease, diesel & coolants.
- Resistant to changeable weather conditions, temperature extremes (periodically up to 350°C) and UV radiation.
- Highly and permanently elastic sealing properties

### Base materials

#### Approved for use in:

- Glass
- Protected metals (aluminium, brass, copper, steel, zinc-plated metal sheet)
- Ceramics
- Glaze
- Concrete
- Masonry
- Plastics
- Metal Sheet & Profiles

## Installation guide



1. The surface, that silicone will be applied on, should be clean, free of dust, grease, rust, remains of old seal and other substances that might weaken the cohesion.
2. Prior to application of silicone protect edges with masking tape
3. Cut the tip of the cartridge, leaving part of the thread. Screw the applicator on to the thread, then cut at the required angle to give an aperture width suited to the joint.
4. Use manual or pneumatic gun applicator.
5. Applied silicone may be smoothed with a spatula or similar tool. Moisten the spatula first in special wetting agent or detergent solution.
6. The silicone hardens by reaction with moisture from the air, so ensure well-ventilated conditions.
7. After completing the application, wipe tools with a paper towel and clean with solvent.

## Technical Data

Parameter		Value	Methods
Application temperature	[°C]	+5 ÷ +40	
Coverage	-	18 linear meters of 4x4 mm joint per one 300 ml cartridge	
Thermal resistance (upon hardening)	[°C]	-40 ÷ +250	
Pretreatment time	[min]	10	
Curing time	[mm/24h]	2	
Hardening system	-	one-component-crosslinking with air humidity	
Hardening type	-	acidic-acetate	
Density	[kg/dm <sup>3</sup> ]	1.28	
Shore A hardness	-	33	SHORE A Method, after 14 days
Ultimate elongation	[%]	180	ISO 8339, +23°C
Shrinkage	[%]	6	
Allowable deformation	[%]	25	
Packaging	-	300 ml cartridge	
<b>R-SL-TK-05-EN</b>			
Colour	-	red	
<b>R-SL-TK-07-EN</b>			
Colour	-	black	

Parameter		Value
Storage temperature	[°C]	+5 ÷ +35
Storage	[month]	18
	-	In originally closed containers, in cool and dry places.

## Product commercial data

Product Code	Colour	Quantity [pcs]			Weight [kg]			Bar Codes
		Box	Outer	Pallet	Box	Outer	Pallet	
R-SL-TK-05-EN	red	15	15	1260	7.5	7.5	660.0	5906675286709
R-SL-TK-07-EN	black	15	15	1260	7.5	7.5	660.0	5906675286716